



ACRYLIC LATEX GLOSS TEXTURE

EFF - Series

DESCRIPTION	SYSTEM RECOMMENDATION																														
<p>A premium quality exterior/interior vinyl/acrylic emulsion based medium texture finish. This product has been formulated to provide excellent exterior durability, hiding of imperfections, esthetic looks and tough flexible finish.</p>	<p><u>Asbestos Siding, Gypsum Board:</u></p> <table border="0"> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Acrylic Gloss Texture</td> <td>2 Coats</td> <td>150 Microns DFT per coat</td> </tr> </table>	Masonry Conditioner	1 Coat	25 Microns DFT	Acrylic Gloss Texture	2 Coats	150 Microns DFT per coat																								
Masonry Conditioner	1 Coat	25 Microns DFT																													
Acrylic Gloss Texture	2 Coats	150 Microns DFT per coat																													
RECOMMENDED USES	<u>Concrete Block and Masonry Surfaces:</u>																														
<p>For use over prepared substrate such as drywall, plaster, vinyl sidings, plywood, concrete block and other masonry and metal surfaces in architectural application.</p>	<table border="0"> <tr> <td>Recommended Primers</td> <td>1 Coat</td> <td>As Recommended</td> </tr> <tr> <td>Acrylic Gloss Texture</td> <td>2 Coats</td> <td>150 Microns DFT per coat</td> </tr> </table>	Recommended Primers	1 Coat	As Recommended	Acrylic Gloss Texture	2 Coats	150 Microns DFT per coat																								
Recommended Primers	1 Coat	As Recommended																													
Acrylic Gloss Texture	2 Coats	150 Microns DFT per coat																													
CHARACTERISTICS	<u>Recommended Primers:</u>																														
<table border="0"> <tr> <td>Color:</td> <td>Wide range of colors available</td> </tr> <tr> <td>Finish:</td> <td>Gloss</td> </tr> <tr> <td>Volume Solid:</td> <td>50.0% ± 2%</td> </tr> <tr> <td>Specific Gravity:</td> <td>1.17 KGs / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>150 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>2.85 m² / KG</td> </tr> <tr> <td>Flash Point:</td> <td>94 °C</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 1 - 1½ Hours</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>Hard Dry: 24 Hours</td> </tr> <tr> <td> </td> <td></td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Water</td> </tr> </table>	Color:	Wide range of colors available	Finish:	Gloss	Volume Solid:	50.0% ± 2%	Specific Gravity:	1.17 KGs / ltr	Recommended DFT:	150 Microns	Spreading Rate@DFT:	2.85 m ² / KG	Flash Point:	94 °C	Drying Schedule:	Dry to Touch: 1 - 1½ Hours	@ 25 °C/R.H.50	Hard Dry: 24 Hours	 		Shelf Life:	18 months, unopened at 25 °C	Reducer/Clean Up:	Water	<ul style="list-style-type: none"> • Acrylic Primer Sealer (S) or (W) • Wall & Wood Primer • Latex Wall Primer <p><u>Wood/Fiber Board:</u></p> <table border="0"> <tr> <td>Wall & Wood Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Acrylic Gloss Texture</td> <td>2 Coats</td> <td>150 Microns DFT per coat</td> </tr> </table> <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>	Wall & Wood Primer	1 Coat	50 Microns DFT	Acrylic Gloss Texture	2 Coats	150 Microns DFT per coat
Color:	Wide range of colors available																														
Finish:	Gloss																														
Volume Solid:	50.0% ± 2%																														
Specific Gravity:	1.17 KGs / ltr																														
Recommended DFT:	150 Microns																														
Spreading Rate@DFT:	2.85 m ² / KG																														
Flash Point:	94 °C																														
Drying Schedule:	Dry to Touch: 1 - 1½ Hours																														
@ 25 °C/R.H.50	Hard Dry: 24 Hours																														
Shelf Life:	18 months, unopened at 25 °C																														
Reducer/Clean Up:	Water																														
Wall & Wood Primer	1 Coat	50 Microns DFT																													
Acrylic Gloss Texture	2 Coats	150 Microns DFT per coat																													
APPLICATION PROCEDURES	SPECIAL TIPS																														
<p><u>Surface Preparation:</u> Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for concrete, plaster, cement, etc. is to allow curing for 30 days. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p> <p><u>Application Methods:</u></p> <table border="0"> <tr> <td>Conventional Spray:</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Airless Spray:</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduction not recommended</td> </tr> </table>	Conventional Spray:	Reduce up to 12% with water	Airless Spray:	Reduce up to 12% with water	Brush/Roller:	Reduction not recommended	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p> <p><u>SAFETY PRECAUTIONS</u></p> <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																								
Conventional Spray:	Reduce up to 12% with water																														
Airless Spray:	Reduce up to 12% with water																														
Brush/Roller:	Reduction not recommended																														