



# HI-BUILD TEXTURE

EQF – W660

DESCRIPTION	SYSTEM RECOMMENDATION																																	
<p>A premium quality exterior/interior vinyl/acrylic emulsion based texture pressed finish. This product has been formulated to provide excellent exterior durability, hiding of imperfections, for application by roller and spray that gives tough finish.</p>	<p><b>Asbestos Siding, Gypsum Board:</b></p> <table border="0"> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Hi-Build Texture</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table>	Masonry Conditioner	1 Coat	25 Microns DFT	Hi-Build Texture	1 Coat	250 Microns DFT	Recommended Topcoats	2 Coats	As Recommended																								
Masonry Conditioner	1 Coat	25 Microns DFT																																
Hi-Build Texture	1 Coat	250 Microns DFT																																
Recommended Topcoats	2 Coats	As Recommended																																
RECOMMENDED USES																																		
<p>For use over prepared substrate such as drywall, plaster, vinyl sidings, plywood, concrete block and other masonry and metal surfaces in architectural application.</p>	<p><b>Concrete Block:</b></p> <table border="0"> <tr> <td>Heavy Duty Block Filler</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Hi-Build Texture</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Acrylic Primer Sealer</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table>	Heavy Duty Block Filler	1 Coat	250 Microns DFT	Hi-Build Texture	1 Coat	250 Microns DFT	Acrylic Primer Sealer	1 Coat	25 Microns DFT	Recommended Topcoats	2 Coats	As Recommended																					
Heavy Duty Block Filler	1 Coat	250 Microns DFT																																
Hi-Build Texture	1 Coat	250 Microns DFT																																
Acrylic Primer Sealer	1 Coat	25 Microns DFT																																
Recommended Topcoats	2 Coats	As Recommended																																
CHARACTERISTICS																																		
<table border="0"> <tr> <td><b>Color:</b></td> <td>White &amp; Light Colors</td> </tr> <tr> <td><b>Finish:</b></td> <td>Flat</td> </tr> <tr> <td><b>Volume Solid:</b></td> <td>50.0% ± 2%</td> </tr> <tr> <td><b>Specific Gravity:</b></td> <td>1.5 ± 0.1%</td> </tr> <tr> <td><b>Recommended DFT:</b></td> <td>250 Microns</td> </tr> <tr> <td><b>Spreading Rate@DFT:</b></td> <td>1 m<sup>2</sup> / KG</td> </tr> <tr> <td><b>Flash Point:</b></td> <td>94 °C</td> </tr> <tr> <td><b>Drying Schedule:</b></td> <td><b>Dry to Touch:</b> 1 - 1½ Hours</td> </tr> <tr> <td><b>@ 25 °C/R.H.50</b></td> <td><b>Hard Dry:</b> 24 Hours</td> </tr> <tr> <td> </td> <td></td> </tr> <tr> <td><b>Shelf Life:</b></td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td><b>Reducer/Clean Up:</b></td> <td>Water</td> </tr> </table>	<b>Color:</b>	White & Light Colors	<b>Finish:</b>	Flat	<b>Volume Solid:</b>	50.0% ± 2%	<b>Specific Gravity:</b>	1.5 ± 0.1%	<b>Recommended DFT:</b>	250 Microns	<b>Spreading Rate@DFT:</b>	1 m <sup>2</sup> / KG	<b>Flash Point:</b>	94 °C	<b>Drying Schedule:</b>	<b>Dry to Touch:</b> 1 - 1½ Hours	<b>@ 25 °C/R.H.50</b>	<b>Hard Dry:</b> 24 Hours	 		<b>Shelf Life:</b>	18 months, unopened at 25 °C	<b>Reducer/Clean Up:</b>	Water	<p><b>Wood/Fiber Board:</b></p> <table border="0"> <tr> <td>Wall &amp; Wood Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Hi-Build Texture</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table> <p><b>Topcoats Recommended:</b></p> <ul style="list-style-type: none"> <li>• Exterior Plastic Emulsion</li> <li>• Sherwin Fine Emulsion</li> <li>• Flat Tone Latex Finish</li> <li>• Latex Satin Finish</li> <li>• Weatherclad (Gloss, Semigloss, Flat)</li> <li>• Alkyd Enamel (Gloss, Semigloss, Flat)</li> <li>• Sheracryl (Gloss, Semigloss, Flat, Clear)</li> <li>• Hi-Build Aliphatic Polyurethane</li> </ul> <p>*For further information on topcoats recommended please refer to Sherwin Williams Saudi Arabia Painting &amp; Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>	Wall & Wood Primer	1 Coat	50 Microns DFT	Hi-Build Texture	1 Coat	250 Microns DFT	Recommended Topcoats	2 Coats	As Recommended
<b>Color:</b>	White & Light Colors																																	
<b>Finish:</b>	Flat																																	
<b>Volume Solid:</b>	50.0% ± 2%																																	
<b>Specific Gravity:</b>	1.5 ± 0.1%																																	
<b>Recommended DFT:</b>	250 Microns																																	
<b>Spreading Rate@DFT:</b>	1 m <sup>2</sup> / KG																																	
<b>Flash Point:</b>	94 °C																																	
<b>Drying Schedule:</b>	<b>Dry to Touch:</b> 1 - 1½ Hours																																	
<b>@ 25 °C/R.H.50</b>	<b>Hard Dry:</b> 24 Hours																																	
<b>Shelf Life:</b>	18 months, unopened at 25 °C																																	
<b>Reducer/Clean Up:</b>	Water																																	
Wall & Wood Primer	1 Coat	50 Microns DFT																																
Hi-Build Texture	1 Coat	250 Microns DFT																																
Recommended Topcoats	2 Coats	As Recommended																																
APPLICATION PROCEDURES	SPECIAL TIPS																																	
<p><b>Surface Preparation:</b> Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for concrete, plaster, cement, etc. is to allow curing for 30 days. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email <a href="mailto:ask@sherwinwilliams.ae">ask@sherwinwilliams.ae</a></p>																																	
<p><b>Application Methods:</b></p> <table border="0"> <tr> <td><b>Conventional Spray:</b></td> <td>Reduce up to 12% with water (to obtain pressed pattern after 5-7 minutes of spraying, press the wet sprayed paint with Texture Roller)</td> </tr> <tr> <td><b>Airless Spray:</b></td> <td>Reduce up to 12% with water</td> </tr> <tr> <td><b>Brush/Roller:</b></td> <td>Reduction not recommended</td> </tr> </table>	<b>Conventional Spray:</b>	Reduce up to 12% with water (to obtain pressed pattern after 5-7 minutes of spraying, press the wet sprayed paint with Texture Roller)	<b>Airless Spray:</b>	Reduce up to 12% with water	<b>Brush/Roller:</b>	Reduction not recommended	SAFETY PRECAUTIONS																											
<b>Conventional Spray:</b>	Reduce up to 12% with water (to obtain pressed pattern after 5-7 minutes of spraying, press the wet sprayed paint with Texture Roller)																																	
<b>Airless Spray:</b>	Reduce up to 12% with water																																	
<b>Brush/Roller:</b>	Reduction not recommended																																	
	<p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																																	