



# NEBULA FINISH

NCF – Series

DESCRIPTION	SYSTEM RECOMMENDATION																								
<p>Superior quality washable multicolored exterior/interior vinyl/acrylic emulsion flat finish. This product has been formulated to provide excellent exterior durability, washability, stain resistance and a unique multi flecks interior design look.</p>	<p><b><u>Iron and Steel:</u></b></p> <table border="0"> <tr> <td>Latex Metal Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Flat Tone Latex Finish</td> <td>1 Coat</td> <td>30 Microns DFT</td> </tr> <tr> <td>Nebula Finish</td> <td>1 Coat</td> <td>As Desirable</td> </tr> <tr> <td>Kemlac Gloss Clear</td> <td>1 Coat</td> <td>30 Microns DFT</td> </tr> </table>	Latex Metal Primer	1 Coat	50 Microns DFT	Flat Tone Latex Finish	1 Coat	30 Microns DFT	Nebula Finish	1 Coat	As Desirable	Kemlac Gloss Clear	1 Coat	30 Microns DFT												
Latex Metal Primer	1 Coat	50 Microns DFT																							
Flat Tone Latex Finish	1 Coat	30 Microns DFT																							
Nebula Finish	1 Coat	As Desirable																							
Kemlac Gloss Clear	1 Coat	30 Microns DFT																							
RECOMMENDED USES																									
<p>For use over prepared substrate such as drywall, plaster, vinyl sidings, plywood, concrete block and other masonry and metal surfaces in architectural application.</p>	<p><b><u>Asbestos Siding, Gypsum Board:</u></b></p> <table border="0"> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Flat Tone Latex Finish</td> <td>1 Coat</td> <td>30 Microns DFT</td> </tr> <tr> <td>Nebula Finish</td> <td>1 Coat</td> <td>As Desirable</td> </tr> <tr> <td>Kemlac Gloss Clear</td> <td>1 Coat</td> <td>30 Microns DFT</td> </tr> </table>	Masonry Conditioner	1 Coat	25 Microns DFT	Flat Tone Latex Finish	1 Coat	30 Microns DFT	Nebula Finish	1 Coat	As Desirable	Kemlac Gloss Clear	1 Coat	30 Microns DFT												
Masonry Conditioner	1 Coat	25 Microns DFT																							
Flat Tone Latex Finish	1 Coat	30 Microns DFT																							
Nebula Finish	1 Coat	As Desirable																							
Kemlac Gloss Clear	1 Coat	30 Microns DFT																							
CHARACTERISTICS																									
<table border="0"> <tr> <td><b>Color:</b></td> <td>Wide range of colors available</td> </tr> <tr> <td><b>Finish:</b></td> <td>Flat and smooth</td> </tr> <tr> <td><b>Volume Solid:</b></td> <td>47.75% ± 1%</td> </tr> <tr> <td><b>Specific Gravity:</b></td> <td>1.17 ± 0.15 KG / ltr</td> </tr> <tr> <td><b>Recommended DFT:</b></td> <td>30 Microns</td> </tr> <tr> <td><b>Spreading Rate@DFT:</b></td> <td>1 m<sup>2</sup> / KG</td> </tr> <tr> <td><b>Flash Point:</b></td> <td>94 °C</td> </tr> <tr> <td><b>Drying Schedule:</b></td> <td><b>Dry to Touch:</b> 1 - 1½ Hours</td> </tr> <tr> <td><b>@ 25 °C/R.H.50</b></td> <td><b>To Handle:</b> 4 Hours</td> </tr> <tr> <td></td> <td><b>To Recoat:</b> 4 Hours</td> </tr> <tr> <td><b>Shelf Life:</b></td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td><b>Reducer/Clean Up:</b></td> <td>Water</td> </tr> </table>	<b>Color:</b>	Wide range of colors available	<b>Finish:</b>	Flat and smooth	<b>Volume Solid:</b>	47.75% ± 1%	<b>Specific Gravity:</b>	1.17 ± 0.15 KG / ltr	<b>Recommended DFT:</b>	30 Microns	<b>Spreading Rate@DFT:</b>	1 m <sup>2</sup> / KG	<b>Flash Point:</b>	94 °C	<b>Drying Schedule:</b>	<b>Dry to Touch:</b> 1 - 1½ Hours	<b>@ 25 °C/R.H.50</b>	<b>To Handle:</b> 4 Hours		<b>To Recoat:</b> 4 Hours	<b>Shelf Life:</b>	18 months, unopened at 25 °C	<b>Reducer/Clean Up:</b>	Water	<p><b><u>Previously Painted Surfaces:</u></b> Surfaces should be free from all foreign material. Old paint films must be brush blasted or scuff sanded prior to coating. Unknown old paint surface should be tested for lifting or peeling. If it does, clean to sound substrate and treat as new surface.</p> <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting &amp; Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>
<b>Color:</b>	Wide range of colors available																								
<b>Finish:</b>	Flat and smooth																								
<b>Volume Solid:</b>	47.75% ± 1%																								
<b>Specific Gravity:</b>	1.17 ± 0.15 KG / ltr																								
<b>Recommended DFT:</b>	30 Microns																								
<b>Spreading Rate@DFT:</b>	1 m <sup>2</sup> / KG																								
<b>Flash Point:</b>	94 °C																								
<b>Drying Schedule:</b>	<b>Dry to Touch:</b> 1 - 1½ Hours																								
<b>@ 25 °C/R.H.50</b>	<b>To Handle:</b> 4 Hours																								
	<b>To Recoat:</b> 4 Hours																								
<b>Shelf Life:</b>	18 months, unopened at 25 °C																								
<b>Reducer/Clean Up:</b>	Water																								
APPLICATION PROCEDURES	SPECIAL TIPS																								
<p><b><u>Surface Preparation:</u></b> Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for <b>(1)</b> Iron and Steel – SSPC-SP3-63 <b>(2)</b> Aluminum and Galvanizing – SSPC-SP1-63. <b>(3)</b> Wood to be sanded and/or scraped to a clean smooth surface. Allow weathering of new galvanized steel for six months prior to coating. Mildew must be removed prior to painting by washing with a solution of 1qt. household bleach and 3 quarts warm water.</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email <a href="mailto:ask@sherwinwilliams.ae">ask@sherwinwilliams.ae</a></p>																								
<p><b><u>Application Methods:</u></b></p> <table border="0"> <tr> <td><b>Conventional or Airless Spray:</b></td> <td>Reduce up to 12% with water</td> </tr> <tr> <td><b>Brush/Roller:</b></td> <td>Reduction not recommended</td> </tr> </table>	<b>Conventional or Airless Spray:</b>	Reduce up to 12% with water	<b>Brush/Roller:</b>	Reduction not recommended	SAFETY PRECAUTIONS																				
<b>Conventional or Airless Spray:</b>	Reduce up to 12% with water																								
<b>Brush/Roller:</b>	Reduction not recommended																								
	<p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																								