



# ONE COAT LATEX FINISH

EEF – W560

DESCRIPTION	SYSTEM RECOMMENDATION															
<p>Superior quality exterior/interior emulsion paint with a flat finish. This product has been formulated to provide excellent fade, blister and stain resistance, with good washability.</p>	<p><b>Concrete Blocks:</b></p> <table border="0"> <tr> <td>Recommended Primer</td> <td>1 Coat</td> <td>As Recommended</td> </tr> <tr> <td>Heavy Duty Block Filler <b>or</b></td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Acrylic Latex Putty Int.</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Recommended Primer</td> <td>1 Coat</td> <td>As Recommended</td> </tr> <tr> <td>One Coat Latex Finish</td> <td>1 Coat</td> <td>55 Microns DFT</td> </tr> </table>	Recommended Primer	1 Coat	As Recommended	Heavy Duty Block Filler <b>or</b>	1 Coat	250 Microns DFT	Acrylic Latex Putty Int.	1 Coat	250 Microns DFT	Recommended Primer	1 Coat	As Recommended	One Coat Latex Finish	1 Coat	55 Microns DFT
Recommended Primer	1 Coat	As Recommended														
Heavy Duty Block Filler <b>or</b>	1 Coat	250 Microns DFT														
Acrylic Latex Putty Int.	1 Coat	250 Microns DFT														
Recommended Primer	1 Coat	As Recommended														
One Coat Latex Finish	1 Coat	55 Microns DFT														
RECOMMENDED USES	<p><b>Primers Recommended:</b></p> <ul style="list-style-type: none"> <li>• Acrylic Primer Sealer (S) <b>or</b> (W)</li> <li>• Latex Wall Primer</li> <li>• Wall &amp; Wood Primer</li> </ul>															
<p>For use over prepared substrate such as drywall, plaster, vinyl sidings, plywood, concrete block and other masonry and metal surfaces in architectural application.</p>	<p><b>Iron and Steel:</b></p> <table border="0"> <tr> <td>Latex Metal Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>One Coat Latex Finish</td> <td>1 Coat</td> <td>55 Microns DFT</td> </tr> </table>	Latex Metal Primer	1 Coat	50 Microns DFT	One Coat Latex Finish	1 Coat	55 Microns DFT									
Latex Metal Primer	1 Coat	50 Microns DFT														
One Coat Latex Finish	1 Coat	55 Microns DFT														
CHARACTERISTICS	<p><b>Asbestos Siding, Gypsum Board:</b></p> <table border="0"> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>One Coat Latex Finish</td> <td>1 Coat</td> <td>55 Microns DFT</td> </tr> </table>	Masonry Conditioner	1 Coat	25 Microns DFT	One Coat Latex Finish	1 Coat	55 Microns DFT									
Masonry Conditioner	1 Coat	25 Microns DFT														
One Coat Latex Finish	1 Coat	55 Microns DFT														
<p><b>Color:</b> Wide range of colors available  <b>Finish:</b> Flat  <b>Volume Solid:</b> 37.0% ± 1%  <b>Specific Gravity:</b> 1.34 KG / ltr  <b>Recommended DFT:</b> 55 Microns  <b>Spreading Rate@DFT:</b> 6.72 m<sup>2</sup> / ltr or 25.46 m<sup>2</sup> / US gallon  <b>Flash Point:</b> 94 °C  <b>Drying Schedule:</b>  <b>@ 25 °C/R.H.50</b>  <b>Dry to Touch:</b> 30 Minutes  <b>To Handle:</b> 4 Hours  <b>To Recoat:</b> 4 Hours  <b>Shelf Life:</b> 18 months, unopened at 25 °C  <b>Reducer/Clean Up:</b> Water</p>	<p><b>Aluminum and Galvanized Steel (Self Prime):</b></p> <table border="0"> <tr> <td>One Coat Latex Finish</td> <td>1 Coat</td> <td>55 Microns DFT</td> </tr> </table> <p><b>Wood/Fiber Board:</b></p> <table border="0"> <tr> <td>Wall &amp; Wood Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>One Coat Latex Finish</td> <td>1 Coat</td> <td>55 Microns DFT</td> </tr> </table> <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting &amp; Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>	One Coat Latex Finish	1 Coat	55 Microns DFT	Wall & Wood Primer	1 Coat	50 Microns DFT	One Coat Latex Finish	1 Coat	55 Microns DFT						
One Coat Latex Finish	1 Coat	55 Microns DFT														
Wall & Wood Primer	1 Coat	50 Microns DFT														
One Coat Latex Finish	1 Coat	55 Microns DFT														
APPLICATION PROCEDURES	SPECIAL TIPS															
<p><b>Surface Preparation:</b> Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for (1) Iron and Steel – SSPC-SP3-63 (2) Aluminum and Galvanizing – SSPC-SP1-63. (3) Wood to be sanded and/or scraped to a clean smooth surface. Allow weathering of new galvanized steel for six months prior to coating. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p> <p><b>Application Methods:</b>  <b>Conventional Spray:</b> Reduce up to 12% with water  <b>Airless Spray:</b> Reduce up to 12% with water  <b>Brush/Roller:</b> Reduction not recommended</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email <a href="mailto:ask@sherwinwilliams.ae">ask@sherwinwilliams.ae</a></p> <p><b>SAFETY PRECAUTIONS</b></p> <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>															