



SHERTONE

EAf – W525

DESCRIPTION	SYSTEM RECOMMENDATION																											
<p>Economical quality thixotropic interior acrylic copolymer emulsion paint with a flat finish. This product has been formulated to provide excellent fade, blister and stain resistance, with good washability.</p>	<p>Concrete Blocks:</p> <table border="0"> <tr> <td>Recommended Primer</td> <td>1 Coat</td> <td>As Recommended</td> </tr> <tr> <td>Heavy Duty Block Filler <u>or</u></td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td colspan="3"> </td> </tr> <tr> <td>Acrylic Latex Putty Int.</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Recommended Primer</td> <td>1 Coat</td> <td>As Recommended</td> </tr> <tr> <td>Sheritone</td> <td>2 Coats</td> <td>25 Microns DFT per coat</td> </tr> </table>	Recommended Primer	1 Coat	As Recommended	Heavy Duty Block Filler <u>or</u>	1 Coat	250 Microns DFT				Acrylic Latex Putty Int.	1 Coat	250 Microns DFT	Recommended Primer	1 Coat	As Recommended	Sheritone	2 Coats	25 Microns DFT per coat									
Recommended Primer	1 Coat	As Recommended																										
Heavy Duty Block Filler <u>or</u>	1 Coat	250 Microns DFT																										
Acrylic Latex Putty Int.	1 Coat	250 Microns DFT																										
Recommended Primer	1 Coat	As Recommended																										
Sheritone	2 Coats	25 Microns DFT per coat																										
RECOMMENDED USES	<p>Primers Recommended:</p> <ul style="list-style-type: none"> Acrylic Primer Sealer (S) <u>or</u> (W) Latex Wall Primer Wall & Wood Primer 																											
<p>For use over prepared substrate such as drywall, plaster, vinyl sidings, plywood, concrete block and other masonry and metal surfaces in architectural application.</p>	<p>Iron and Steel:</p> <table border="0"> <tr> <td>Latex Metal Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Sheritone</td> <td>2 Coats</td> <td>25 Microns DFT per coat</td> </tr> </table>	Latex Metal Primer	1 Coat	50 Microns DFT	Sheritone	2 Coats	25 Microns DFT per coat																					
Latex Metal Primer	1 Coat	50 Microns DFT																										
Sheritone	2 Coats	25 Microns DFT per coat																										
CHARACTERISTICS	<p>Asbestos Siding, Gypsum Board:</p> <table border="0"> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Sheritone</td> <td>2 Coats</td> <td>25 Microns DFT per coat</td> </tr> </table>	Masonry Conditioner	1 Coat	25 Microns DFT	Sheritone	2 Coats	25 Microns DFT per coat																					
Masonry Conditioner	1 Coat	25 Microns DFT																										
Sheritone	2 Coats	25 Microns DFT per coat																										
<table border="0"> <tr> <td>Color:</td> <td>Wide range of colors available</td> </tr> <tr> <td>Finish:</td> <td>Flat</td> </tr> <tr> <td>Volume Solid:</td> <td>34.0% ± 2%</td> </tr> <tr> <td>Specific Gravity:</td> <td>1.5 KG / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>25 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>13.60 m² / ltr or 51.48 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>94 °C</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 30 Minutes</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 4 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 2 Hours</td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Water</td> </tr> </table>	Color:	Wide range of colors available	Finish:	Flat	Volume Solid:	34.0% ± 2%	Specific Gravity:	1.5 KG / ltr	Recommended DFT:	25 Microns	Spreading Rate@DFT:	13.60 m ² / ltr or 51.48 m ² / US gallon	Flash Point:	94 °C	Drying Schedule:	Dry to Touch: 30 Minutes	@ 25 °C/R.H.50	To Handle: 4 Hours		To Recoat: 2 Hours	Shelf Life:	18 months, unopened at 25 °C	Reducer/Clean Up:	Water	<p>Aluminum and Galvanized Steel (Self Prime):</p> <table border="0"> <tr> <td>Sheritone</td> <td>2 Coats</td> <td>25 Microns DFT per coat</td> </tr> </table>	Sheritone	2 Coats	25 Microns DFT per coat
Color:	Wide range of colors available																											
Finish:	Flat																											
Volume Solid:	34.0% ± 2%																											
Specific Gravity:	1.5 KG / ltr																											
Recommended DFT:	25 Microns																											
Spreading Rate@DFT:	13.60 m ² / ltr or 51.48 m ² / US gallon																											
Flash Point:	94 °C																											
Drying Schedule:	Dry to Touch: 30 Minutes																											
@ 25 °C/R.H.50	To Handle: 4 Hours																											
	To Recoat: 2 Hours																											
Shelf Life:	18 months, unopened at 25 °C																											
Reducer/Clean Up:	Water																											
Sheritone	2 Coats	25 Microns DFT per coat																										
<p>APPLICATION PROCEDURES</p>	<p>SPECIAL TIPS</p>																											
<p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for (1) Iron and Steel – SSPC-SP3-63 (2) Aluminum and Galvanizing – SSPC-SP1-63. (3) Wood to be sanded and/or scraped to a clean smooth surface. Allow weathering of new galvanized steel for six months prior to coating. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p> <p>Application Methods:</p> <table border="0"> <tr> <td>Conventional or Airless</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Spray:</td> <td></td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduction not recommended</td> </tr> </table>	Conventional or Airless	Reduce up to 12% with water	Spray:		Brush/Roller:	Reduction not recommended	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p>																					
Conventional or Airless	Reduce up to 12% with water																											
Spray:																												
Brush/Roller:	Reduction not recommended																											
<p>SAFETY PRECAUTIONS</p> <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																												