



TEXTURE PRESSED PATTERN

EPF – Series

DESCRIPTION	SYSTEM RECOMMENDATION												
<p>A premium quality exterior/interior vinyl/acrylic emulsion based texture pressed finish. This product has been formulated to provide excellent exterior durability, hiding of imperfections, esthetic looks and tough flexible finish.</p>	<p>Asbestos Siding, Gypsum Board:</p> <table border="0"> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Texture Pressed Pattern</td> <td>1 Coat</td> <td>150 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table>	Masonry Conditioner	1 Coat	25 Microns DFT	Texture Pressed Pattern	1 Coat	150 Microns DFT	Recommended Topcoats	2 Coats	As Recommended			
Masonry Conditioner	1 Coat	25 Microns DFT											
Texture Pressed Pattern	1 Coat	150 Microns DFT											
Recommended Topcoats	2 Coats	As Recommended											
RECOMMENDED USES	<p>Concrete Block:</p> <table border="0"> <tr> <td>Heavy Duty Block Filler</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Texture Pressed Pattern</td> <td>1 Coat</td> <td>150 Microns DFT</td> </tr> <tr> <td>Acrylic Primer Sealer</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table>	Heavy Duty Block Filler	1 Coat	250 Microns DFT	Texture Pressed Pattern	1 Coat	150 Microns DFT	Acrylic Primer Sealer	1 Coat	25 Microns DFT	Recommended Topcoats	2 Coats	As Recommended
Heavy Duty Block Filler	1 Coat	250 Microns DFT											
Texture Pressed Pattern	1 Coat	150 Microns DFT											
Acrylic Primer Sealer	1 Coat	25 Microns DFT											
Recommended Topcoats	2 Coats	As Recommended											
<p>For use over prepared substrate such as drywall, plaster, vinyl sidings, plywood, concrete block and other masonry and metal surfaces in architectural application.</p>	<p>Wood/Fiber Board:</p> <table border="0"> <tr> <td>Wall & Wood Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Texture Pressed Pattern</td> <td>1 Coat</td> <td>150 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table>	Wall & Wood Primer	1 Coat	50 Microns DFT	Texture Pressed Pattern	1 Coat	150 Microns DFT	Recommended Topcoats	2 Coats	As Recommended			
Wall & Wood Primer	1 Coat	50 Microns DFT											
Texture Pressed Pattern	1 Coat	150 Microns DFT											
Recommended Topcoats	2 Coats	As Recommended											
CHARACTERISTICS	<p>Topcoats Recommended:</p> <ul style="list-style-type: none"> • Exterior Plastic Emulsion • Sherwin Fine Emulsion • Flat Tone Latex Finish • Latex Satin Finish • Weatherclad (Gloss, Semigloss, Flat) • Alkyd Enamel (Gloss, Semigloss, Flat) • Sheracryl (Gloss, Semigloss, Flat, Clear) • Hi-Build Aliphatic Polyurethane (Clear, Enamel) 												
<p>Color: Wide range of colors available Finish: Texture Finish Volume Solid: 48.0% ± 2% Specific Gravity: 1.17 KG / ltr Recommended DFT: 150 Microns Spreading Rate@DFT: 1 m² / KG Flash Point: 94 °C Drying Schedule: Dry to Touch: 1- 1½Hours @ 25 °C/R.H.50 Hard Dry: 24 Hours</p> <p>Shelf Life: 18 months, unopened at 25 °C Reducer/Clean Up: Water</p>	<p>Topcoats Recommended:</p> <ul style="list-style-type: none"> • Exterior Plastic Emulsion • Sherwin Fine Emulsion • Flat Tone Latex Finish • Latex Satin Finish • Weatherclad (Gloss, Semigloss, Flat) • Alkyd Enamel (Gloss, Semigloss, Flat) • Sheracryl (Gloss, Semigloss, Flat, Clear) • Hi-Build Aliphatic Polyurethane (Clear, Enamel) <p>*For further information on topcoats recommended please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>												
APPLICATION PROCEDURES	SPECIAL TIPS												
<p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for concrete, plaster, cement, etc. is to allow curing for 30 days. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p>												
<p>Application Methods:</p> <p>Conventional Spray: Reduce up to 12% with water Airless Spray: Reduce up to 12% with water Brush/Roller: Reduction not recommended</p>	<p>SAFETY PRECAUTIONS</p> <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>												