



CONCRETE & TERRAZO SEALER

SKF - C228

| DESCRIPTION | SYSTEM RECOMMENDATION | | | | | | | | | | | | | | | | | | | | | | | | | |
|---|--|--|-----------------------|--|------------------------------|--|--|-------------------------|-------------------------|----------------|----------------------------|--|---------------------|-------|-------------------------|---------------------------------|-----------------------|---------------------------|--|---------------------------|--------------------|------------------------------|--------------------------|--------------------|--|--------------|
| <p>A carefully formulated acrylic clear sealer for interior/exterior application, that provides excellent acid and alkali resistance with superior adhesion to multiple substrates.</p> | <p>Concrete/Masonry Surface, Natural Wood/Fiberboard:</p> <table border="0"> <tr> <td>Concrete & Terrazo Slr.</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Acrylic Latex Putty Interior</td> <td>1 Coat</td> <td>250 Microns</td> </tr> <tr> <td>Concrete & Terrazo Slr.</td> <td>2 Coats</td> <td>25 Microns DFT</td> </tr> <tr> <td colspan="3">Recommended Topcoats</td> </tr> </table> | Concrete & Terrazo Slr. | 1 Coat | 25 Microns DFT | Acrylic Latex Putty Interior | 1 Coat | 250 Microns | Concrete & Terrazo Slr. | 2 Coats | 25 Microns DFT | Recommended Topcoats | | | | | | | | | | | | | | | |
| Concrete & Terrazo Slr. | 1 Coat | 25 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | | |
| Acrylic Latex Putty Interior | 1 Coat | 250 Microns | | | | | | | | | | | | | | | | | | | | | | | | |
| Concrete & Terrazo Slr. | 2 Coats | 25 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | | |
| Recommended Topcoats | | | | | | | | | | | | | | | | | | | | | | | | | | |
| RECOMMENDED USES | <p>Previously Painted Masonry:</p> <table border="0"> <tr> <td>Concrete & Terrazo Slr.</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Acrylic Latex Putty Interior</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Concrete & Terrazo Slr.</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td colspan="3">Recommended Topcoats</td> </tr> </table> | Concrete & Terrazo Slr. | 1 Coat | 25 Microns DFT | Acrylic Latex Putty Interior | 1 Coat | 250 Microns DFT | Concrete & Terrazo Slr. | 1 Coat | 25 Microns DFT | Recommended Topcoats | | | | | | | | | | | | | | | |
| Concrete & Terrazo Slr. | 1 Coat | 25 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | | |
| Acrylic Latex Putty Interior | 1 Coat | 250 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | | |
| Concrete & Terrazo Slr. | 1 Coat | 25 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | | |
| Recommended Topcoats | | | | | | | | | | | | | | | | | | | | | | | | | | |
| <p>For use over prepared substrate such as drywall, cinder block, plaster, asbestos, wood, concrete block, marble and other masonry surfaces in architectural application.</p> | <p>Topcoats Recommended:</p> <ul style="list-style-type: none"> • Exterior/Interior Plastic Emulsion • Sherwin Fine Emulsion • Flat Tone Latex Finish • Weatherclad (Gloss, Semigloss, Flat) • Latex Satin Finish • Alkyd Enamels (Flat, Eggshell, Semigloss, Hi-Gloss) • Sheracryl Acrylic Enamel (Gloss, Semigloss, Flat, Clear) | | | | | | | | | | | | | | | | | | | | | | | | | |
| CHARACTERISTICS | <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p> | | | | | | | | | | | | | | | | | | | | | | | | | |
| <table border="0"> <tr> <td>Color:</td> <td>Clear</td> </tr> <tr> <td>Finish:</td> <td>Glossy</td> </tr> <tr> <td>Volume Solid:</td> <td>14.15% ± 1%</td> </tr> <tr> <td>Specific Gravity:</td> <td>0.89 KGs / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>25 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>5.64 m² / ltr or 21.34 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>26 °F</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 30 Minutes</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 4 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 2 Hours</td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Thinner YTF – K078</td> </tr> </table> | Color: | Clear | Finish: | Glossy | Volume Solid: | 14.15% ± 1% | Specific Gravity: | 0.89 KGs / ltr | Recommended DFT: | 25 Microns | Spreading Rate@DFT: | 5.64 m ² / ltr or 21.34 m ² / US gallon | Flash Point: | 26 °F | Drying Schedule: | Dry to Touch: 30 Minutes | @ 25 °C/R.H.50 | To Handle: 4 Hours | | To Recoat: 2 Hours | Shelf Life: | 18 months, unopened at 25 °C | Reducer/Clean Up: | Thinner YTF – K078 | <th data-bbox="783 1431 1520 1469">SPECIAL TIPS</th> | SPECIAL TIPS |
| Color: | Clear | | | | | | | | | | | | | | | | | | | | | | | | | |
| Finish: | Glossy | | | | | | | | | | | | | | | | | | | | | | | | | |
| Volume Solid: | 14.15% ± 1% | | | | | | | | | | | | | | | | | | | | | | | | | |
| Specific Gravity: | 0.89 KGs / ltr | | | | | | | | | | | | | | | | | | | | | | | | | |
| Recommended DFT: | 25 Microns | | | | | | | | | | | | | | | | | | | | | | | | | |
| Spreading Rate@DFT: | 5.64 m ² / ltr or 21.34 m ² / US gallon | | | | | | | | | | | | | | | | | | | | | | | | | |
| Flash Point: | 26 °F | | | | | | | | | | | | | | | | | | | | | | | | | |
| Drying Schedule: | Dry to Touch: 30 Minutes | | | | | | | | | | | | | | | | | | | | | | | | | |
| @ 25 °C/R.H.50 | To Handle: 4 Hours | | | | | | | | | | | | | | | | | | | | | | | | | |
| | To Recoat: 2 Hours | | | | | | | | | | | | | | | | | | | | | | | | | |
| Shelf Life: | 18 months, unopened at 25 °C | | | | | | | | | | | | | | | | | | | | | | | | | |
| Reducer/Clean Up: | Thinner YTF – K078 | | | | | | | | | | | | | | | | | | | | | | | | | |
| <p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Concrete, brick and other similar surfaces should be cured for about six weeks before painting. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p> | <p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p> | | | | | | | | | | | | | | | | | | | | | | | | | |
| <p>Application Methods:</p> <table border="0"> <tr> <td>Conventional Spray:</td> <td>Reduce up to 50% with industrial thinner</td> </tr> <tr> <td>Airless Spray:</td> <td>Reduce up to 50% with industrial thinner</td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduce up to 50% with industrial thinner</td> </tr> </table> | Conventional Spray: | Reduce up to 50% with industrial thinner | Airless Spray: | Reduce up to 50% with industrial thinner | Brush/Roller: | Reduce up to 50% with industrial thinner | <th data-bbox="783 1650 1520 1688">SAFETY PRECAUTIONS</th> | SAFETY PRECAUTIONS | | | | | | | | | | | | | | | | | | |
| Conventional Spray: | Reduce up to 50% with industrial thinner | | | | | | | | | | | | | | | | | | | | | | | | | |
| Airless Spray: | Reduce up to 50% with industrial thinner | | | | | | | | | | | | | | | | | | | | | | | | | |
| Brush/Roller: | Reduce up to 50% with industrial thinner | | | | | | | | | | | | | | | | | | | | | | | | | |
| | <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p> | | | | | | | | | | | | | | | | | | | | | | | | | |