



MASONRY CONDITIONER

SWF – V004

DESCRIPTION	SYSTEM RECOMMENDATION																								
<p>A carefully formulated acrylic clear sealer for interior/exterior application, that provides excellent acid and alkali resistance with superior adhesion to multiple substrates.</p>	<p>Concrete & Cinder Block/Masonry:</p> <table border="0"> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Acrylic Latex Putty Int.</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>1 Coat</td> <td>As Recommended</td> </tr> </table>	Masonry Conditioner	1 Coat	50 Microns DFT	Acrylic Latex Putty Int.	1 Coat	250 Microns DFT	Masonry Conditioner	1 Coat	50 Microns DFT	Recommended Topcoats	1 Coat	As Recommended												
Masonry Conditioner	1 Coat	50 Microns DFT																							
Acrylic Latex Putty Int.	1 Coat	250 Microns DFT																							
Masonry Conditioner	1 Coat	50 Microns DFT																							
Recommended Topcoats	1 Coat	As Recommended																							
RECOMMENDED USES																									
<p>For use over prepared substrate such as drywall, cinder block, plaster, asbestos, concrete block and other masonry surfaces in architectural application.</p>	<p>Previously Painted Masonry:</p> <table border="0"> <tr> <td>Masonry Conditioner</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>1 Coat</td> <td>As Recommended</td> </tr> </table> <p>Topcoats Recommended:</p> <ul style="list-style-type: none"> • Weatherclad (Gloss, Semigloss, Flat Finish) • Flat Tone Latex Finish • Plastic Emulsions (Interior/Exterior) • Sheracryl (Gloss, Semigloss, Flat, Clear) • Alkyd Enamels (Gloss, Semigloss, Flat) <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>	Masonry Conditioner	1 Coat	50 Microns DFT	Recommended Topcoats	1 Coat	As Recommended																		
Masonry Conditioner	1 Coat	50 Microns DFT																							
Recommended Topcoats	1 Coat	As Recommended																							
CHARACTERISTICS																									
<table border="0"> <tr> <td>Color:</td> <td>Clear</td> </tr> <tr> <td>Finish:</td> <td>Glossy</td> </tr> <tr> <td>Volume Solid:</td> <td>27% ± 1%</td> </tr> <tr> <td>Specific Gravity:</td> <td>0.88 KGs / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>50 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>5.40 m² / ltr or 20.44 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>40 °F</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 1 Hour</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 4 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 12 Hours</td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>YTF – K099</td> </tr> </table>	Color:	Clear	Finish:	Glossy	Volume Solid:	27% ± 1%	Specific Gravity:	0.88 KGs / ltr	Recommended DFT:	50 Microns	Spreading Rate@DFT:	5.40 m ² / ltr or 20.44 m ² / US gallon	Flash Point:	40 °F	Drying Schedule:	Dry to Touch: 1 Hour	@ 25 °C/R.H.50	To Handle: 4 Hours		To Recoat: 12 Hours	Shelf Life:	18 months, unopened at 25 °C	Reducer/Clean Up:	YTF – K099	
Color:	Clear																								
Finish:	Glossy																								
Volume Solid:	27% ± 1%																								
Specific Gravity:	0.88 KGs / ltr																								
Recommended DFT:	50 Microns																								
Spreading Rate@DFT:	5.40 m ² / ltr or 20.44 m ² / US gallon																								
Flash Point:	40 °F																								
Drying Schedule:	Dry to Touch: 1 Hour																								
@ 25 °C/R.H.50	To Handle: 4 Hours																								
	To Recoat: 12 Hours																								
Shelf Life:	18 months, unopened at 25 °C																								
Reducer/Clean Up:	YTF – K099																								
APPLICATION PROCEDURES	SPECIAL TIPS																								
<p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Concrete, brick and other similar surfaces should be cured for about six weeks before painting. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p> <p>Application Methods:</p> <table border="0"> <tr> <td>Conventional Spray:</td> <td>Reduce 10% with paint thinner</td> </tr> <tr> <td>Airless Spray:</td> <td>Reduce 10% with paint thinner</td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduction not recommended</td> </tr> </table>	Conventional Spray:	Reduce 10% with paint thinner	Airless Spray:	Reduce 10% with paint thinner	Brush/Roller:	Reduction not recommended	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p> <p>SAFETY PRECAUTIONS</p> <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																		
Conventional Spray:	Reduce 10% with paint thinner																								
Airless Spray:	Reduce 10% with paint thinner																								
Brush/Roller:	Reduction not recommended																								