



ACRYLIC SEALER CLEAR

EYF – T049

DESCRIPTION	SYSTEM RECOMMENDATION																								
<p>A finest quality clear acrylic latex sealer, designed for use on exterior, drywall, masonry/concrete surfaces and chalky surfaces, providing excellent alkali resistance and holdout for any recommended topcoat.</p>	<p>Concrete Block/Masonry:</p> <table border="0"> <tr> <td>Acrylic Sealer Clear</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Heavy Duty Block Filler</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Acrylic Sealer Clear</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Recommended Topcoat</td> <td>2 Coats</td> <td>Respective DFT per coat</td> </tr> </table>	Acrylic Sealer Clear	1 Coat	25 Microns DFT	Heavy Duty Block Filler	1 Coat	250 Microns DFT	Acrylic Sealer Clear	1 Coat	25 Microns DFT	Recommended Topcoat	2 Coats	Respective DFT per coat												
Acrylic Sealer Clear	1 Coat	25 Microns DFT																							
Heavy Duty Block Filler	1 Coat	250 Microns DFT																							
Acrylic Sealer Clear	1 Coat	25 Microns DFT																							
Recommended Topcoat	2 Coats	Respective DFT per coat																							
RECOMMENDED USES																									
<p>For use over prepared substrate such as drywall, chalky surfaces, plaster, concrete block and other masonry surfaces in architectural application.</p>	<p>Dry Wall:</p> <table border="0"> <tr> <td>Acrylic Sealer Clear</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Recommended Topcoat</td> <td>2 Coats</td> <td>Respective DFT per coat</td> </tr> </table>	Acrylic Sealer Clear	1 Coat	25 Microns DFT	Recommended Topcoat	2 Coats	Respective DFT per coat																		
Acrylic Sealer Clear	1 Coat	25 Microns DFT																							
Recommended Topcoat	2 Coats	Respective DFT per coat																							
CHARACTERISTICS																									
<table border="0"> <tr> <td>Color:</td> <td>Clear, Transparent</td> </tr> <tr> <td>Finish:</td> <td>Gloss</td> </tr> <tr> <td>Volume Solid:</td> <td>28.0% ± 1%</td> </tr> <tr> <td>Specific Gravity:</td> <td>1.07 KGs / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>25 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>11.20 m² / ltr or 42.40 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>94 °C</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 1 Hour</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 4 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 3 Hours</td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Water</td> </tr> </table>	Color:	Clear, Transparent	Finish:	Gloss	Volume Solid:	28.0% ± 1%	Specific Gravity:	1.07 KGs / ltr	Recommended DFT:	25 Microns	Spreading Rate@DFT:	11.20 m ² / ltr or 42.40 m ² / US gallon	Flash Point:	94 °C	Drying Schedule:	Dry to Touch: 1 Hour	@ 25 °C/R.H.50	To Handle: 4 Hours		To Recoat: 3 Hours	Shelf Life:	18 months, unopened at 25 °C	Reducer/Clean Up:	Water	<p>Topcoats Recommended:</p> <ul style="list-style-type: none"> • Exterior Plastic Emulsion • Sherwin Fine Emulsion • Flat Tone Latex Finish • Weatherclad (Gloss, Semigloss, Flat) • Latex Satin Finish <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>
Color:	Clear, Transparent																								
Finish:	Gloss																								
Volume Solid:	28.0% ± 1%																								
Specific Gravity:	1.07 KGs / ltr																								
Recommended DFT:	25 Microns																								
Spreading Rate@DFT:	11.20 m ² / ltr or 42.40 m ² / US gallon																								
Flash Point:	94 °C																								
Drying Schedule:	Dry to Touch: 1 Hour																								
@ 25 °C/R.H.50	To Handle: 4 Hours																								
	To Recoat: 3 Hours																								
Shelf Life:	18 months, unopened at 25 °C																								
Reducer/Clean Up:	Water																								
APPLICATION PROCEDURES	SPECIAL TIPS																								
<p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Concrete, brick and other similar surfaces should be cured for about six weeks before painting. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p>																								
<p>Application Methods:</p> <table border="0"> <tr> <td>Conventional Spray:</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Airless Spray:</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduction not recommended</td> </tr> </table>	Conventional Spray:	Reduce up to 12% with water	Airless Spray:	Reduce up to 12% with water	Brush/Roller:	Reduction not recommended	SAFETY PRECAUTIONS																		
Conventional Spray:	Reduce up to 12% with water																								
Airless Spray:	Reduce up to 12% with water																								
Brush/Roller:	Reduction not recommended																								
	<p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																								