



LATEX ACRYLIC PRIMER/SEALER

EHF – W814

| DESCRIPTION | SYSTEM RECOMMENDATION | | | | | | | | | | | | | | | | | | | | | | | | |
|---|--|-----------------------------|-----------------------|-----------------------------|-----------------------------------|---------------------------|--------------------------|------------------------------|-------------------------|-----------------|-----------------------------|---|---------------------|----------------------|-------------------------|-----------------------------|-----------------------|---------------------------|--|---------------------------|--------------------|------------------------------|--------------------------|-------|--|
| <p>A finest quality primer and sealer, designed for use on interior and exterior, drywall and masonry/concrete surfaces, providing excellent alkali resistance and holdout for any recommended topcoat.</p> | <p>Concrete Block/Masonry:</p> <table border="0"> <tr> <td>Latex Acrylic Primer/Sealer</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Heavy Duty Block Filler or</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Acrylic Latex Putty Interior</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Latex Acrylic Primer/Sealer</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table> | Latex Acrylic Primer/Sealer | 1 Coat | 25 Microns DFT | Heavy Duty Block Filler or | 1 Coat | 250 Microns DFT | Acrylic Latex Putty Interior | 1 Coat | 250 Microns DFT | Latex Acrylic Primer/Sealer | 1 Coat | 25 Microns DFT | Recommended Topcoats | 2 Coats | As Recommended | | | | | | | | | |
| Latex Acrylic Primer/Sealer | 1 Coat | 25 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | |
| Heavy Duty Block Filler or | 1 Coat | 250 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | |
| Acrylic Latex Putty Interior | 1 Coat | 250 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | |
| Latex Acrylic Primer/Sealer | 1 Coat | 25 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | |
| Recommended Topcoats | 2 Coats | As Recommended | | | | | | | | | | | | | | | | | | | | | | | |
| RECOMMENDED USES | | | | | | | | | | | | | | | | | | | | | | | | | |
| <p>For use over prepared substrate such as drywall, cinder block, plaster, concrete block and other masonry surfaces in architectural application.</p> | <p>Dry Wall:</p> <table border="0"> <tr> <td>Latex Acrylic Primer/Sealer</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Heavy Duty Block Filler or</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Acrylic Latex Putty Interior</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table> | Latex Acrylic Primer/Sealer | 1 Coat | 25 Microns DFT | Heavy Duty Block Filler or | 1 Coat | 250 Microns DFT | Acrylic Latex Putty Interior | 1 Coat | 250 Microns DFT | Recommended Topcoats | 2 Coats | As Recommended | | | | | | | | | | | | |
| Latex Acrylic Primer/Sealer | 1 Coat | 25 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | |
| Heavy Duty Block Filler or | 1 Coat | 250 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | |
| Acrylic Latex Putty Interior | 1 Coat | 250 Microns DFT | | | | | | | | | | | | | | | | | | | | | | | |
| Recommended Topcoats | 2 Coats | As Recommended | | | | | | | | | | | | | | | | | | | | | | | |
| CHARACTERISTICS | <p>Topcoats Recommended:</p> <ul style="list-style-type: none"> • Exterior/Interior Plastic Emulsion • Sherwin Fine Emulsion • Flat Tone Latex Finish • Weatherclad (Gloss, Semigloss, Flat) • Latex Satin Finish <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p> | | | | | | | | | | | | | | | | | | | | | | | | |
| <table border="0"> <tr> <td>Color:</td> <td>White</td> </tr> <tr> <td>Finish:</td> <td>Flat</td> </tr> <tr> <td>Volume Solid:</td> <td>33.0% ± 2%</td> </tr> <tr> <td>Specific Gravity:</td> <td>1.10 KGs / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>25 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>13.2 m²/ltr or 49.96 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>94 °C</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 1 Hour</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 4 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 4 Hours</td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Water</td> </tr> </table> | Color: | White | Finish: | Flat | Volume Solid: | 33.0% ± 2% | Specific Gravity: | 1.10 KGs / ltr | Recommended DFT: | 25 Microns | Spreading Rate@DFT: | 13.2 m ² /ltr or 49.96 m ² / US gallon | Flash Point: | 94 °C | Drying Schedule: | Dry to Touch: 1 Hour | @ 25 °C/R.H.50 | To Handle: 4 Hours | | To Recoat: 4 Hours | Shelf Life: | 18 months, unopened at 25 °C | Reducer/Clean Up: | Water | |
| Color: | White | | | | | | | | | | | | | | | | | | | | | | | | |
| Finish: | Flat | | | | | | | | | | | | | | | | | | | | | | | | |
| Volume Solid: | 33.0% ± 2% | | | | | | | | | | | | | | | | | | | | | | | | |
| Specific Gravity: | 1.10 KGs / ltr | | | | | | | | | | | | | | | | | | | | | | | | |
| Recommended DFT: | 25 Microns | | | | | | | | | | | | | | | | | | | | | | | | |
| Spreading Rate@DFT: | 13.2 m ² /ltr or 49.96 m ² / US gallon | | | | | | | | | | | | | | | | | | | | | | | | |
| Flash Point: | 94 °C | | | | | | | | | | | | | | | | | | | | | | | | |
| Drying Schedule: | Dry to Touch: 1 Hour | | | | | | | | | | | | | | | | | | | | | | | | |
| @ 25 °C/R.H.50 | To Handle: 4 Hours | | | | | | | | | | | | | | | | | | | | | | | | |
| | To Recoat: 4 Hours | | | | | | | | | | | | | | | | | | | | | | | | |
| Shelf Life: | 18 months, unopened at 25 °C | | | | | | | | | | | | | | | | | | | | | | | | |
| Reducer/Clean Up: | Water | | | | | | | | | | | | | | | | | | | | | | | | |
| APPLICATION PROCEDURES | SPECIAL TIPS | | | | | | | | | | | | | | | | | | | | | | | | |
| <p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Concrete, brick and other similar surfaces should be cured for about six weeks before painting. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p> | <p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p> | | | | | | | | | | | | | | | | | | | | | | | | |
| <p>Application Methods:</p> <table border="0"> <tr> <td>Conventional Spray:</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Airless Spray:</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduction not recommended</td> </tr> </table> | Conventional Spray: | Reduce up to 12% with water | Airless Spray: | Reduce up to 12% with water | Brush/Roller: | Reduction not recommended | SAFETY PRECAUTIONS | | | | | | | | | | | | | | | | | | |
| Conventional Spray: | Reduce up to 12% with water | | | | | | | | | | | | | | | | | | | | | | | | |
| Airless Spray: | Reduce up to 12% with water | | | | | | | | | | | | | | | | | | | | | | | | |
| Brush/Roller: | Reduction not recommended | | | | | | | | | | | | | | | | | | | | | | | | |
| | <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p> | | | | | | | | | | | | | | | | | | | | | | | | |