



SHERWIN MASONRY SEALER

EHF – W816

DESCRIPTION	SYSTEM RECOMMENDATION																								
<p>A quality economical latex sealer, designed for use on interior, drywall and masonry/concrete surfaces, providing excellent hold for any recommended topcoat.</p>	<p>Concrete Block/Masonry:</p> <table border="0"> <tr> <td>Sherwin Masonry Sealer</td> <td>1 Coat</td> <td>No film (25 Microns DFT)</td> </tr> <tr> <td>Interior Acrylic Latex Putty <u>or</u></td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Heavy Duty Block Filler</td> <td>1 Coat</td> <td>250 Microns DFT</td> </tr> <tr> <td>Sherwin Masonry Sealer</td> <td>1 Coat</td> <td>No film (25 Microns DFT)</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>Respective DFT per coat</td> </tr> </table>	Sherwin Masonry Sealer	1 Coat	No film (25 Microns DFT)	Interior Acrylic Latex Putty <u>or</u>	1 Coat	250 Microns DFT	Heavy Duty Block Filler	1 Coat	250 Microns DFT	Sherwin Masonry Sealer	1 Coat	No film (25 Microns DFT)	Recommended Topcoats	2 Coats	Respective DFT per coat									
Sherwin Masonry Sealer	1 Coat	No film (25 Microns DFT)																							
Interior Acrylic Latex Putty <u>or</u>	1 Coat	250 Microns DFT																							
Heavy Duty Block Filler	1 Coat	250 Microns DFT																							
Sherwin Masonry Sealer	1 Coat	No film (25 Microns DFT)																							
Recommended Topcoats	2 Coats	Respective DFT per coat																							
RECOMMENDED USES																									
<p>For use over prepared substrate such as drywall, plaster, concrete block and other masonry surfaces in architectural application.</p>	<p>Dry Wall:</p> <table border="0"> <tr> <td>Sherwin Masonry Sealer</td> <td>1 Coat</td> <td>No film (25 Microns DFT)</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>Respective DFT per coat</td> </tr> </table>	Sherwin Masonry Sealer	1 Coat	No film (25 Microns DFT)	Recommended Topcoats	2 Coats	Respective DFT per coat																		
Sherwin Masonry Sealer	1 Coat	No film (25 Microns DFT)																							
Recommended Topcoats	2 Coats	Respective DFT per coat																							
CHARACTERISTICS																									
<table border="0"> <tr> <td>Color:</td> <td>Opaque</td> </tr> <tr> <td>Finish:</td> <td>Flat</td> </tr> <tr> <td>Volume Solid:</td> <td>22.0% ± 1%</td> </tr> <tr> <td>Specific Gravity:</td> <td>1.05 KGs / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>No film (depends on porosity)</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>08.00 – 10.00 m² /ltr or 30.28 – 37.85 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>94 °C</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 1 Hour</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 4 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 4 Hours</td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Water</td> </tr> </table>	Color:	Opaque	Finish:	Flat	Volume Solid:	22.0% ± 1%	Specific Gravity:	1.05 KGs / ltr	Recommended DFT:	No film (depends on porosity)	Spreading Rate@DFT:	08.00 – 10.00 m ² /ltr or 30.28 – 37.85 m ² / US gallon	Flash Point:	94 °C	Drying Schedule:	Dry to Touch: 1 Hour	@ 25 °C/R.H.50	To Handle: 4 Hours		To Recoat: 4 Hours	Shelf Life:	18 months, unopened at 25 °C	Reducer/Clean Up:	Water	<p>Topcoats Recommended:</p> <ul style="list-style-type: none"> • Shertone • Exterior Plastic Emulsion • Sherwin Fine Emulsion • Flat Tone Latex Finish • Weatherclad (Gloss, Semigloss, Flat) • Latex Satin Finish <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>
Color:	Opaque																								
Finish:	Flat																								
Volume Solid:	22.0% ± 1%																								
Specific Gravity:	1.05 KGs / ltr																								
Recommended DFT:	No film (depends on porosity)																								
Spreading Rate@DFT:	08.00 – 10.00 m ² /ltr or 30.28 – 37.85 m ² / US gallon																								
Flash Point:	94 °C																								
Drying Schedule:	Dry to Touch: 1 Hour																								
@ 25 °C/R.H.50	To Handle: 4 Hours																								
	To Recoat: 4 Hours																								
Shelf Life:	18 months, unopened at 25 °C																								
Reducer/Clean Up:	Water																								
APPLICATION PROCEDURES	SPECIAL TIPS																								
<p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Concrete, brick and other similar surfaces should be cured for about six weeks before painting. Mildew must be removed prior to painting by washing with a solution of 1 quart household bleach and 3 quarts warm water.</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p>																								
<p>Application Methods:</p> <table border="0"> <tr> <td>Conventional Spray:</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Airless Spray:</td> <td>Reduce up to 12% with water</td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduction not recommended</td> </tr> </table>	Conventional Spray:	Reduce up to 12% with water	Airless Spray:	Reduce up to 12% with water	Brush/Roller:	Reduction not recommended	SAFETY PRECAUTIONS																		
Conventional Spray:	Reduce up to 12% with water																								
Airless Spray:	Reduce up to 12% with water																								
Brush/Roller:	Reduction not recommended																								
	<p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																								