



ELASTIC CRACK FILLER

ETF – W590

DESCRIPTION	SYSTEM RECOMMENDATION																								
<p>An Elastomeric acrylic copolymer coating for protection of exterior surfaces. It is waterproofing system that provides excellent flexibility, durability and weather resistance. It provides protection to the roof from wind driven rain with easy application and cleaning, and also fills cracks.</p>	<p>Concrete/Plaster/Masonry/Asbestos Protective:</p> <table border="0"> <tr> <td>Acrylic Primer Sealer (S)</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>or</td> <td></td> <td></td> </tr> <tr> <td>Latex Wall Primer</td> <td>1 Coat</td> <td>25 Microns DFT</td> </tr> <tr> <td>Elastic Crack Filler</td> <td>2 Coats</td> <td>250 Microns DFT per coat</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table>	Acrylic Primer Sealer (S)	1 Coat	25 Microns DFT	or			Latex Wall Primer	1 Coat	25 Microns DFT	Elastic Crack Filler	2 Coats	250 Microns DFT per coat	Recommended Topcoats	2 Coats	As Recommended									
Acrylic Primer Sealer (S)	1 Coat	25 Microns DFT																							
or																									
Latex Wall Primer	1 Coat	25 Microns DFT																							
Elastic Crack Filler	2 Coats	250 Microns DFT per coat																							
Recommended Topcoats	2 Coats	As Recommended																							
RECOMMENDED USES																									
<p>For use over prepared substrate such as masonry, bricks, plaster, concrete block and other masonry and metal surfaces in civil application. It protects expanded polyurethane foam from deterioration by weather and by UV rays.</p>	<p>Recommended Topcoats:</p> <ul style="list-style-type: none"> • Flat Tone Latex Finish • Weather-Clad (Flat, Satin, Semigloss, Gloss) • Sher-Shield Satin Emulsion • Sheracryl Acrylic Enamel (Flat, Semigloss, Gloss) 																								
CHARACTERISTICS	<p>Crack Repairs:</p>																								
<table border="0"> <tr> <td>Color:</td> <td>White</td> </tr> <tr> <td>Finish:</td> <td>Flat and smooth</td> </tr> <tr> <td>Volume Solid:</td> <td>55% ± 1%</td> </tr> <tr> <td>Specific Gravity:</td> <td>1.48 KGs / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>250 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>2.2 m² / ltr or 8.32 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>94 °C</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 1 – 1½ Hours</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 4 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 24 Hours</td> </tr> <tr> <td>Shelf Life:</td> <td>9 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Water</td> </tr> </table>	Color:	White	Finish:	Flat and smooth	Volume Solid:	55% ± 1%	Specific Gravity:	1.48 KGs / ltr	Recommended DFT:	250 Microns	Spreading Rate@DFT:	2.2 m ² / ltr or 8.32 m ² / US gallon	Flash Point:	94 °C	Drying Schedule:	Dry to Touch: 1 – 1½ Hours	@ 25 °C/R.H.50	To Handle: 4 Hours		To Recoat: 24 Hours	Shelf Life:	9 months, unopened at 25 °C	Reducer/Clean Up:	Water	<p>No Greater than 1/4" Using a broad knife apply one coat of any commercial Elastic patching material as a tape bedding compound; apply a single layer of perforated nylon or polyester tape, top dress all exposed tape with Elastic patching material. Ensure that the sealing is perfect. Allow half an hour to dry Finally apply two coats of Elastic Crack Filler at 250 Microns DFT / coat.</p> <p>Cracks Greater than 1/4" Must be first sealed with repair mortar or Sherwin Williams "Kem Cati Coat Epoxy Filler". Allow minimum cure time to dry thoroughly for cement mortar 24 hours and for Epoxy 6 hours (Minimum) then apply two coats of Elastic Crack Filler at 250 Microns DFT/Coat.</p> <p>Expansion Joints or Gaps Subjected to Movement: Prior to sealing the joints apply by brush Elastic Crack Filler evenly inside the joint. Then seal the joints with polysulfide sealant, backing rod must be used to control the sealant depth. All the joints must be reinforced by embedding a strip of fiberglass tape in the wet Elastic Crack Filler . Finally apply two coats of Elastic Crack Filler over the whole surface including the taped surface at 250 Microns DFT/Coat.</p>
Color:	White																								
Finish:	Flat and smooth																								
Volume Solid:	55% ± 1%																								
Specific Gravity:	1.48 KGs / ltr																								
Recommended DFT:	250 Microns																								
Spreading Rate@DFT:	2.2 m ² / ltr or 8.32 m ² / US gallon																								
Flash Point:	94 °C																								
Drying Schedule:	Dry to Touch: 1 – 1½ Hours																								
@ 25 °C/R.H.50	To Handle: 4 Hours																								
	To Recoat: 24 Hours																								
Shelf Life:	9 months, unopened at 25 °C																								
Reducer/Clean Up:	Water																								
APPLICATION PROCEDURES																									
<p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for (1) Concrete, Masonry – ensure proper curing. Mildew must be removed prior to painting by washing with a solution of 1qt. household bleach and 3 quarts warm water.</p> <p>Application Methods:</p> <p>Special blade, Steel edged spatula, or scraper</p>	<p>Badly Deteriorated Concrete Plastered Surfaces or Massive Repairs: Surfaces should be free from all foreign material. Remove all loose plaster. Repair with commercial vinyl latex cement mortar. If the surface is chalky or powdery apply one coat Sherwin Williams Masonry Conditioner or Sherwin Williams Latex Wall Primer 25 Microns DFT then apply two coats of Elastic Crack Filler 250 Microns DFT/coat.</p> <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>																								
SAFETY PRECAUTIONS	SPECIAL TIPS																								
<p>Apply under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>	<p>Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p>																								