



# FAST DRY ALKYD ENAMEL

JDF Gloss Series  
 JBF Semigloss Series  
 JAF Flat Series

DESCRIPTION	SYSTEM RECOMMENDATION																							
<p>Premium quality styrenated alkyd enamel designed for interior/exterior application on multiple substrates finishing and refinishing of industrial, construction and farm equipments.</p>	<p><b><u>Iron, Steel, Aluminum, Galvanized Steel:</u></b></p> <table border="0"> <tr> <td>Recommended Primer</td> <td>1 Coat</td> <td>As Recommended</td> </tr> <tr> <td>Fast Dry Alkyd Enamel</td> <td>2 Coats</td> <td>38 Microns DFT per coat</td> </tr> </table>	Recommended Primer	1 Coat	As Recommended	Fast Dry Alkyd Enamel	2 Coats	38 Microns DFT per coat																	
Recommended Primer	1 Coat	As Recommended																						
Fast Dry Alkyd Enamel	2 Coats	38 Microns DFT per coat																						
<p><b>RECOMMENDED USES</b></p>	<p><b><u>Primers Recommended:</u></b></p>																							
<p>For use over prepared substrate such as steel, aluminum, galvanized steel, steel fabricated parts, toys, and tools.</p>	<ul style="list-style-type: none"> <li>• Anti-Rust Metal Primer</li> <li>• Red Oxide Metal Primer</li> <li>• Tile Clad II Primer</li> <li>• Zinc Chromate Primer</li> </ul>																							
<p><b>CHARACTERISTICS</b></p>	<p><b><u>Iron, Steel, Aluminum, Galvanized Steel (Self Prime):</u></b></p>																							
<table border="0"> <tr> <td><b>Color:</b></td> <td>Wide range of colors available</td> </tr> <tr> <td><b>Finish:</b></td> <td>Gloss/Semigloss/Flat</td> </tr> <tr> <td><b>Volume Solid:</b></td> <td>45% ± 2%</td> </tr> <tr> <td><b>Specific Gravity:</b></td> <td>1.11 KGs / ltr</td> </tr> <tr> <td><b>Recommended DFT:</b></td> <td>38 Microns</td> </tr> <tr> <td><b>Spreading Rate@DFT:</b></td> <td>11.86 m<sup>2</sup> / ltr or 44.90 m<sup>2</sup> / US gallon</td> </tr> <tr> <td><b>Flash Point:</b></td> <td>40 °C</td> </tr> <tr> <td><b>Drying Schedule: @ 25 °C/R.H.50</b></td> <td><b>Dry to Touch:</b> 10 Minutes <b>To Handle:</b> 12 Hours <b>To Recoat:</b> 30 Minutes</td> </tr> <tr> <td><b>Shelf Life:</b></td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td><b>Reducer/Clean Up:</b></td> <td>Thinner YTF – K002</td> </tr> </table>	<b>Color:</b>	Wide range of colors available	<b>Finish:</b>	Gloss/Semigloss/Flat	<b>Volume Solid:</b>	45% ± 2%	<b>Specific Gravity:</b>	1.11 KGs / ltr	<b>Recommended DFT:</b>	38 Microns	<b>Spreading Rate@DFT:</b>	11.86 m <sup>2</sup> / ltr or 44.90 m <sup>2</sup> / US gallon	<b>Flash Point:</b>	40 °C	<b>Drying Schedule: @ 25 °C/R.H.50</b>	<b>Dry to Touch:</b> 10 Minutes <b>To Handle:</b> 12 Hours <b>To Recoat:</b> 30 Minutes	<b>Shelf Life:</b>	18 months, unopened at 25 °C	<b>Reducer/Clean Up:</b>	Thinner YTF – K002	<table border="0"> <tr> <td>Fast Dry Alkyd Enamel</td> <td>2 Coats</td> <td>38 Microns DFT per coat</td> </tr> </table> <p><b><u>Previously Painted Surfaces:</u></b> Surfaces should be free from all foreign material. Old paint films must be brush blasted or scuff sanded prior to coating. Unknown old paint surface should be tested for lifting or peeling. If it does, clean to sound substrate and treat as new surface.</p> <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting &amp; Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>	Fast Dry Alkyd Enamel	2 Coats	38 Microns DFT per coat
<b>Color:</b>	Wide range of colors available																							
<b>Finish:</b>	Gloss/Semigloss/Flat																							
<b>Volume Solid:</b>	45% ± 2%																							
<b>Specific Gravity:</b>	1.11 KGs / ltr																							
<b>Recommended DFT:</b>	38 Microns																							
<b>Spreading Rate@DFT:</b>	11.86 m <sup>2</sup> / ltr or 44.90 m <sup>2</sup> / US gallon																							
<b>Flash Point:</b>	40 °C																							
<b>Drying Schedule: @ 25 °C/R.H.50</b>	<b>Dry to Touch:</b> 10 Minutes <b>To Handle:</b> 12 Hours <b>To Recoat:</b> 30 Minutes																							
<b>Shelf Life:</b>	18 months, unopened at 25 °C																							
<b>Reducer/Clean Up:</b>	Thinner YTF – K002																							
Fast Dry Alkyd Enamel	2 Coats	38 Microns DFT per coat																						
<p><b>APPLICATION PROCEDURES</b></p>	<p><b>SPECIAL TIPS</b></p>																							
<p><b><u>Surface Preparation:</u></b> Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for <b>(1)</b> Iron and Steel – SSPC-SP2 or SP3 <b>(2)</b> Aluminum and Galvanizing – SSPC-SP1 <b>(3)</b> Concrete should be cured, dry and clean. Allow weathering of new galvanized steel for six months prior to coating.</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email <a href="mailto:ask@sherwinwilliams.ae">ask@sherwinwilliams.ae</a></p>																							
<p><b><u>Application Methods:</u></b></p> <table border="0"> <tr> <td><b>Conventional Spray:</b></td> <td>Reduce 5% with thinner</td> </tr> <tr> <td><b>Airless Spray:</b></td> <td>Reduce as required for suitable spray</td> </tr> <tr> <td><b>Brush/Roller:</b></td> <td>Reduction not recommended</td> </tr> </table>	<b>Conventional Spray:</b>	Reduce 5% with thinner	<b>Airless Spray:</b>	Reduce as required for suitable spray	<b>Brush/Roller:</b>	Reduction not recommended	<p><b><u>SAFETY PRECAUTIONS</u></b></p> <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																	
<b>Conventional Spray:</b>	Reduce 5% with thinner																							
<b>Airless Spray:</b>	Reduce as required for suitable spray																							
<b>Brush/Roller:</b>	Reduction not recommended																							