



HI-BUILD CHLORINATED RUBBER ENAMEL

QBF - Series

DESCRIPTION	SYSTEM RECOMMENDATION																														
<p>A chemical resistant chlorinated rubber based enamel for interior/exterior protection of metal and concrete substrates. It provides severe chemical and moisture resistance with superior adhesion to these substrates.</p>	<p>Iron and Steel:</p> <table border="0"> <tr> <td>Hi-Build Chlorinated Rubber Primer</td> <td>1 Coat</td> <td>75 Microns DFT</td> </tr> <tr> <td>Hi-Build Chlorinated Rubber Enamel</td> <td>2 Coats</td> <td>75 Microns DFT per coat</td> </tr> </table>	Hi-Build Chlorinated Rubber Primer	1 Coat	75 Microns DFT	Hi-Build Chlorinated Rubber Enamel	2 Coats	75 Microns DFT per coat																								
Hi-Build Chlorinated Rubber Primer	1 Coat	75 Microns DFT																													
Hi-Build Chlorinated Rubber Enamel	2 Coats	75 Microns DFT per coat																													
RECOMMENDED USES																															
<p>For use over prepared steel, iron, aluminum, and galvanized metal, concrete block, paper mills, laundries, food processing, dairies.</p>	<p>Aluminum and Galvanized Metal:</p> <table border="0"> <tr> <td>Wash Primer Green</td> <td>1 Coat</td> <td>07 Microns DFT</td> </tr> <tr> <td>Hi-Build Chlorinated Rubber Primer</td> <td>1 Coat</td> <td>75 Microns DFT</td> </tr> <tr> <td>Hi-Build Chlorinated Rubber Enamel</td> <td>2 Coats</td> <td>75 Microns DFT per coat</td> </tr> </table>	Wash Primer Green	1 Coat	07 Microns DFT	Hi-Build Chlorinated Rubber Primer	1 Coat	75 Microns DFT	Hi-Build Chlorinated Rubber Enamel	2 Coats	75 Microns DFT per coat																					
Wash Primer Green	1 Coat	07 Microns DFT																													
Hi-Build Chlorinated Rubber Primer	1 Coat	75 Microns DFT																													
Hi-Build Chlorinated Rubber Enamel	2 Coats	75 Microns DFT per coat																													
CHARACTERISTICS																															
<table border="0"> <tr> <td>Color:</td> <td>Wide range of colors</td> </tr> <tr> <td>Finish:</td> <td>Semigloss</td> </tr> <tr> <td>Volume Solid:</td> <td>34% ± 1%</td> </tr> <tr> <td>Specific Gravity:</td> <td>1.19 KGs / ltr ± 2%</td> </tr> <tr> <td>Recommended DFT:</td> <td>75 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>4.53 m² / ltr or 17.16 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>26 °C</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 15 Minutes</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 2 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 1 Hour</td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Industrial thinner YTF – K099</td> </tr> </table>	Color:	Wide range of colors	Finish:	Semigloss	Volume Solid:	34% ± 1%	Specific Gravity:	1.19 KGs / ltr ± 2%	Recommended DFT:	75 Microns	Spreading Rate@DFT:	4.53 m ² / ltr or 17.16 m ² / US gallon	Flash Point:	26 °C	Drying Schedule:	Dry to Touch: 15 Minutes	@ 25 °C/R.H.50	To Handle: 2 Hours		To Recoat: 1 Hour	Shelf Life:	18 months, unopened at 25 °C	Reducer/Clean Up:	Industrial thinner YTF – K099	<p>Concrete Block/Masonry Surface:</p> <table border="0"> <tr> <td>Recommended Primers/Fillers</td> <td>1 Coat</td> <td>As Recommended</td> </tr> <tr> <td>Hi-Build Chlorinated Rubber Enamel</td> <td>2 Coats</td> <td>75 Microns DFT per coat</td> </tr> </table> <p>Recommended Primers/Fillers:</p> <ul style="list-style-type: none"> • Kem Epoxy Clear Primer Sealer • Kem Cati-Coat Epoxy Filler Sealer • Hi-Build Chlorinated Rubber Primer • Acrylic Primer Sealer (S) or (W) <p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>	Recommended Primers/Fillers	1 Coat	As Recommended	Hi-Build Chlorinated Rubber Enamel	2 Coats	75 Microns DFT per coat
Color:	Wide range of colors																														
Finish:	Semigloss																														
Volume Solid:	34% ± 1%																														
Specific Gravity:	1.19 KGs / ltr ± 2%																														
Recommended DFT:	75 Microns																														
Spreading Rate@DFT:	4.53 m ² / ltr or 17.16 m ² / US gallon																														
Flash Point:	26 °C																														
Drying Schedule:	Dry to Touch: 15 Minutes																														
@ 25 °C/R.H.50	To Handle: 2 Hours																														
	To Recoat: 1 Hour																														
Shelf Life:	18 months, unopened at 25 °C																														
Reducer/Clean Up:	Industrial thinner YTF – K099																														
Recommended Primers/Fillers	1 Coat	As Recommended																													
Hi-Build Chlorinated Rubber Enamel	2 Coats	75 Microns DFT per coat																													
APPLICATION PROCEDURES	SPECIAL TIPS																														
<p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for (1) Iron and Steel – SSPC-SP2 or SP3 (2) Aluminum and Galvanizing – SSPC-SP1. (3) Concrete should be well cured before applying. Allow weathering of new galvanized steel for six months prior to coating.</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p>																														
<p>Application Methods:</p> <table border="0"> <tr> <td>Conventional Spray:</td> <td>Reduce 10% with industrial thinner</td> </tr> <tr> <td>Airless Spray:</td> <td>Reduce 10% with industrial thinner</td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduction not recommended</td> </tr> </table>	Conventional Spray:	Reduce 10% with industrial thinner	Airless Spray:	Reduce 10% with industrial thinner	Brush/Roller:	Reduction not recommended	SAFETY PRECAUTIONS																								
Conventional Spray:	Reduce 10% with industrial thinner																														
Airless Spray:	Reduce 10% with industrial thinner																														
Brush/Roller:	Reduction not recommended																														
	<p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																														