



SHERFLEX 2000

UHF – B789

DESCRIPTION	SYSTEM RECOMMENDATION	
<p>Sherflex 2000 is an asphaltic high build, self bonding, flexible coating which is rust preventive and water resistant. Sherflex 2000 will surface dry, and resist cracking.</p>	<p><u>Iron, Steel (Buried structures in soil):</u></p> <p>Sherflex 2000 1 - 2 Coats 50 Microns DFT per coat</p>	
RECOMMENDED USES	<p><u>Iron, Steel (Immersion service):</u></p> <p>Sherflex 2000 1 - 2 Coats 50 Microns DFT per coat</p>	
<p>For use over prepared substrate such as steel, aluminum, galvanizing, plywood, concrete and masonry, manholes, pipeline, and water ducts.</p>	<p><u>Concrete and masonry - foundations:</u></p> <p>Sherflex 2000 1 - 2 Coats 50 Microns DFT per coat</p>	
CHARACTERISTICS	<p><u>Previously Painted Surfaces:</u> Surfaces should be free from all foreign material. Old paint films must be brush blasted or scuff sanded prior to coating. Unknown old paint surface should be tested for lifting or peeling. If it does, clean to sound substrate and treat as new surface.</p> <p>*For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>	
<p>Color: Black Finish: Matt Volume Solid: 65% ± 1% Specific Gravity: 1.65 KGs / ltr Recommended DFT: 50 Microns Spreading Rate@DFT: 13 m² / ltr or 49.20 m² / US gallon Flash Point: 35 °C Drying Schedule: @ 25 °C/R.H.50 Dry to Touch: 2 Hours To Handle: 18 Hours To Recoat: 12 Hours Shelf Life: 18 months, unopened at 25 °C Reducer/Clean Up: Paint thinner YTF – K099</p>	<th data-bbox="799 1364 1520 1404">SPECIAL TIPS</th>	SPECIAL TIPS
APPLICATION PROCEDURES	<p><u>Surface Preparation:</u> Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for (1) Iron and Steel – SSPC-SP2 or SP3 (2) Aluminum and Galvanizing – SSPC-SP1 (3) Concrete should be cured, dry and clean. Allow weathering of new galvanized steel for six months prior to coating.</p>	
<p><u>Application Methods:</u></p> <p>Conventional Spray: Reduce 5% with paint thinner Airless Spray: Reduce as required for suitable spray Brush/Roller: Reduction not recommended</p>	SAFETY PRECAUTIONS	
	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p> <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>	