



RED OXIDE METAL PRIMER

PHF – N814

DESCRIPTION	SYSTEM RECOMMENDATION																								
<p>A modified alkyd based anticorrosive red oxide metal primer designed for interior/exterior priming of metal. It provides a sprayable, fast drying and easy to sand smooth surface.</p>	<p>Iron and Steel:</p> <table border="0"> <tr> <td>Red Oxide Metal Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table>	Red Oxide Metal Primer	1 Coat	50 Microns DFT	Recommended Topcoats	2 Coats	As Recommended																		
Red Oxide Metal Primer	1 Coat	50 Microns DFT																							
Recommended Topcoats	2 Coats	As Recommended																							
RECOMMENDED USES	<p>Aluminum and Galvanized Metal:</p> <table border="0"> <tr> <td>Red Oxide Metal Primer</td> <td>1 Coat</td> <td>50 Microns DFT</td> </tr> <tr> <td>Recommended Topcoats</td> <td>2 Coats</td> <td>As Recommended</td> </tr> </table>	Red Oxide Metal Primer	1 Coat	50 Microns DFT	Recommended Topcoats	2 Coats	As Recommended																		
Red Oxide Metal Primer	1 Coat	50 Microns DFT																							
Recommended Topcoats	2 Coats	As Recommended																							
<p>For use over prepared steel, iron, aluminum, and galvanized metal.</p>	<p>Topcoats Recommended:</p> <ul style="list-style-type: none"> • Alkyd Enamel (Gloss, Semigloss, Flat Finish) • Enamel Undercoater • Hi-Build Aliphatic Polyurethane • Epoxy • Plastic Emulsions (Interior/Exterior) • Sheracryl (Gloss, Semigloss, Flat, Clear) • Weatherclad (Gloss, Semigloss, Flat Finish) 																								
CHARACTERISTICS	<p>*For further information on recommended products please refer to Sherwin Williams Saudi Arabia Painting & Coatings System Guide.</p> <p>**For further information on surface preparation methods and application procedures please refer to Sherwin Williams Saudi Arabia Surface Preparation bulletin.</p>																								
<table border="0"> <tr> <td>Color:</td> <td>Red Oxide</td> </tr> <tr> <td>Finish:</td> <td>Matt</td> </tr> <tr> <td>Volume Solid:</td> <td>45% ± 1%</td> </tr> <tr> <td>Specific Gravity:</td> <td>1.32 KGs / ltr</td> </tr> <tr> <td>Recommended DFT:</td> <td>50 Microns</td> </tr> <tr> <td>Spreading Rate@DFT:</td> <td>9 m² / ltr or 34 m² / US gallon</td> </tr> <tr> <td>Flash Point:</td> <td>40 °C</td> </tr> <tr> <td>Drying Schedule:</td> <td>Dry to Touch: 1 Hour</td> </tr> <tr> <td>@ 25 °C/R.H.50</td> <td>To Handle: 24 Hours</td> </tr> <tr> <td></td> <td>To Recoat: 24 Hours</td> </tr> <tr> <td>Shelf Life:</td> <td>18 months, unopened at 25 °C</td> </tr> <tr> <td>Reducer/Clean Up:</td> <td>Paint thinner YTF – K099</td> </tr> </table>	Color:	Red Oxide	Finish:	Matt	Volume Solid:	45% ± 1%	Specific Gravity:	1.32 KGs / ltr	Recommended DFT:	50 Microns	Spreading Rate@DFT:	9 m ² / ltr or 34 m ² / US gallon	Flash Point:	40 °C	Drying Schedule:	Dry to Touch: 1 Hour	@ 25 °C/R.H.50	To Handle: 24 Hours		To Recoat: 24 Hours	Shelf Life:	18 months, unopened at 25 °C	Reducer/Clean Up:	Paint thinner YTF – K099	<p>SPECIAL TIPS</p>
Color:	Red Oxide																								
Finish:	Matt																								
Volume Solid:	45% ± 1%																								
Specific Gravity:	1.32 KGs / ltr																								
Recommended DFT:	50 Microns																								
Spreading Rate@DFT:	9 m ² / ltr or 34 m ² / US gallon																								
Flash Point:	40 °C																								
Drying Schedule:	Dry to Touch: 1 Hour																								
@ 25 °C/R.H.50	To Handle: 24 Hours																								
	To Recoat: 24 Hours																								
Shelf Life:	18 months, unopened at 25 °C																								
Reducer/Clean Up:	Paint thinner YTF – K099																								
<p>Surface Preparation: Surface must be dry, clean and in sound condition. Remove oil, dust, dirt, millscale or other foreign substance to ensure good adhesion. Minimum surface preparation methods to be followed for (1) Iron and Steel – SSPC-SP2 or SP3 (2) Aluminum and Galvanizing – SSPC-SP1. Allow weathering of new galvanized steel for six months prior to coating.</p>	<p>Excessive reduction of material can affect the film build, appearance, and adhesion. Any further specific technical information can be obtained from SWSA if you email ask@sherwinwilliams.ae</p>																								
<p>Application Methods:</p> <table border="0"> <tr> <td>Conventional Spray:</td> <td>Reduce 10% with thinner</td> </tr> <tr> <td>Airless Spray:</td> <td>Reduce 10% with thinner</td> </tr> <tr> <td>Brush/Roller:</td> <td>Reduction not recommended</td> </tr> </table>	Conventional Spray:	Reduce 10% with thinner	Airless Spray:	Reduce 10% with thinner	Brush/Roller:	Reduction not recommended	<p>SAFETY PRECAUTIONS</p> <p>Spray under well-ventilated conditions. Do not breathe or inhale mist. When spraying, wear air mask. Avoid skin contact. Spillage on skin should immediately be removed with suitable cleanser, soap and water. Eyes should be flushed with water and medical attention sought immediately.</p>																		
Conventional Spray:	Reduce 10% with thinner																								
Airless Spray:	Reduce 10% with thinner																								
Brush/Roller:	Reduction not recommended																								